



Eco-Friendly

ACRYLIC EMULSION

Non-Toxic

SINOGRACE

The Chemical Company

Paver Sealer

SA-902 water based polyurethane Sealer

DESCRIPTION

SA-902 is a waterbased polyurethane sealant that penetrates into the slate road and has a hydrophobic function, good abrasion resistance, water resistance, and can inhibit the growth of seaweed and mold.

TYPE

Water based polyurethane polymer

KEY FEATURES

- Ultra wet-look
- UV protection
- Algae and mold inhibitor
- Provides a hydrophobic barrier
- May be applied to a damp surface
- User friendly and environmentally safe
- Excellent joint stabilization, no need for polymeric sand
- Add isocyanate curing agent effect is better

TYPICAL PROPERTIES

Appearance	Milky white liquid
pH	7-9
Solid content	40±1%
Glass Transition Temperature	25°C
Viscosity (25°C)	100-500cP
Cover area	12-20 sqm/L
Diluted ratio	1 parts water :1 part sealer
Dry to touch	0.5-1 hour
Dry to Recoat	4 hours
Dry to traffic	48-72 hours

APPLICATION

- Brick paver
- Stone paver
- Floor coating

STORAGE AND HANDLING

- Available in 200 kg/ barrel or 25 kg/ barrel
- Store products in tightly closed original containers at 5-40°C
- Shelf life: 9 months from delivery date
- According to non-dangerous goods transport

HOW TO USE

1. Pressure Washing: Pressure washes the area to be sealed, ensuring that surfaces are clean and free of oil, efflorescence, laitance or contaminants prior to beginning the sealing process. Remove at least 1 to 2 inches of the old joint sand so new coarse

Anhui Sinograce Chemical Co., Ltd.

Tel: +86-0551-63459511

Email: sales@sinogracechem.com

Add.: Hefei city, Anhui province, China

Mob: +86 15855525589



Eco-Friendly



Non-Toxic

ACRYLIC EMULSION

SINOGRACE

The Chemical Company

sand can be replaced between the paver joints.

2. Rinsing: Rinse the pavers with water. If any acids/cleaners were used during the cleaning phase, make sure that the acids and cleaners are thoroughly rinsed before sealing.

3. Application: SA-902 can be applied even though the pavers are damp. It cannot be applied to pavers in standing water, as the sealer will not cure and stabilize the joint sand. Dilute 1 part water and 1 part sealer for the flood coat and top coat. We recommend multiple coats for extremely absorbent pavers. A slip guard additive may be necessary with additional coats. Using our battery operated pail pump system or pump sprayer, uniformly apply a flood coat of sealer for joint stabilization. Hold sprayer tip 10" – 12" from the paver surface (avoid overspray on adjacent surfaces, rinse any overspray with water). Sealer appears white when applied but dries crystal clear. Make sure to apply sealer consistently to prevent blotching. (Back rolling is recommended for consistency) Pavers with polymeric sand, we recommend two even consistent coats of sealer without flooding the paver joints. Use a leaf blower to blow out any excessive sealer that puddles in the paver joints or low lying areas with textured pavers and or natural stone. Excess sealer may be stored for future use.

Anhui Sinograce Chemical Co., Ltd.

Tel: +86-0551-63459511

Email: sales@sinogracechem.com

Add.: Hefei city, Anhui province, China

Mob: +86 15855525589