

Coupling Agent

Silane coupling agent ZE-22

FEATURE	<ul style="list-style-type: none">● Improve the adhesion of silicone rubber and metal								
TYPE	Diethylamino substituting methyl triethoxysilane								
TYPICAL PROPERTIES	<table><tr><td>Appearance:</td><td>Light yellow transparent liquid</td></tr><tr><td>Boiling range:</td><td>100 ~ 135°C/5mmHg</td></tr><tr><td>Structural formula:</td><td>(C₂H₅)₂NCH₂Si(OC₂H₅)₃</td></tr><tr><td>Solubility:</td><td>Can be dissolved dry alcohol, acetone and other organic solvents, is unstable in water, easily hydrolyzed</td></tr></table>	Appearance:	Light yellow transparent liquid	Boiling range:	100 ~ 135°C/5mmHg	Structural formula:	(C ₂ H ₅) ₂ NCH ₂ Si(OC ₂ H ₅) ₃	Solubility:	Can be dissolved dry alcohol, acetone and other organic solvents, is unstable in water, easily hydrolyzed
Appearance:	Light yellow transparent liquid								
Boiling range:	100 ~ 135°C/5mmHg								
Structural formula:	(C ₂ H ₅) ₂ NCH ₂ Si(OC ₂ H ₅) ₃								
Solubility:	Can be dissolved dry alcohol, acetone and other organic solvents, is unstable in water, easily hydrolyzed								
APPLICATION	<ul style="list-style-type: none">● Silicone rubber curing agent● Curing agent for epoxy resins and tackifier● Used for surface treatment agent silicone rubber and metal bonding time								
STORAGE AND HANDLING	<ul style="list-style-type: none">● Available in 25 kg/drum● Store products in tightly closed original containers at 5-40°C● Shelf life: 12 months from delivery date● According to non-dangerous goods transport								